

RATNA CR1 SPL

Hydrogen controlled iron powder Electrode for welding Creep-Resistant 1Cr-0.5Mo steels.

CLASSIFICATION : AWS/SFA-5.5: E 8016 B2

APPROVAL :

CHARACTERISTICS : A medium heavy coated, hydrogen controlled, iron powder type, all position radiographic quality electrode to weld 1.25% Cr-0.50% Mo steel, having increased working efficiency. Electrode has properties of creep resistance up to 550°C.

APPLICATION :

- 1) Suitable to weld creep resistant steels like Cr-Mo pipelines and plates used in oil refinery.
- 2) Power plants, steam boilers.
- 3) Equipments subjected at high temperature in synthetic chemical units.
- 4) Repair of cast steel components.
- 5) Parts of automobiles & earthmoving machineries.

RE-DRY CONDITION : Re-Dry the electrode at 350°C for 1 hrs before use.

ALL WELD CHEMICAL COMPOSITION %

C	Mn	Si	Cr	Mo	S&P
0.05-0.12	0.90 Max	0.60 max	1.00-1.50	0.40-0.65	0.030 Max.

ALL WELD MECHANICAL PROPERTIES:

YS (N/mm ²)	UTS (N/mm ²)	EL % (l=4d)
460 Min.	550 Min.	19 Min.

DIEMENSION, CURRENT CONDITION & PACKING DATA

Size(mm) (Dia)	Size(inch) (Dia)	Current Condition (DC+) Amps	No. of Pcs./pkt.	No. of Pcs./Case
2.50/ 2.40 X 350	3/ 32" X 14"	60-80	170	640
3.15/ 3.20 X 450	1/ 8" X 18"	100-140	110	440
4.00 X 450	5/ 32" X 18"	140-180	72	288
5.00 X 450	3/ 16" X 18"	190-240	50	200

Customer packing on request.